

TRANSFER OIL

thermoplastic and pte hoses - fittings and assemblies

crimping details

Last updatedMarch 26, 2022

Transfer Oil reserve the rights to introduce improving modifications whenever necessary.
The listed crimping data have been developed in Transfer Oil R&D laboratories and refer to tests carried out on thermoplastic hoses manufactured by Transfer Oil, and specific Transfer Oil approved ferrules and fittings.
Such values are anyway to be considered advisory and not binding for Transfer Oil because the impossibility to consider technical variability like the swaging machine used, the set of crimping dies used, the speed of the crimping process, the tolerances of each single item involved, ect.
For new applications or for hoses, ferrules and fittings not listed in this file please contact us, and we will be happy to help you in finding the best match.

*Transfer Oil si riserva il diritto di introdurre modifiche in qualsiasi momento.
I dati di pressatura qui elencati sono stati determinati nei laboratori R&D di Transfer Oil, e si riferiscono a test condotti su tubazioni termoplastiche prodotte da Transfer Oil, con apposite boccole ed inserti approvati da Transfer Oil.
Tali valori sono comunque da considerarsi indicativi, pertanto non vincolanti per Transfer Oil, a causa dell'impossibilità di considerare tutte le variabili tecniche come il tipo di pressa in uso, il set di punzoni utilizzato, le velocità delle singole operazioni, le tolleranze di ogni particolare, ect.
Per nuove applicazioni o per tubi, boccole e raccordi non presenti in questo elenco, vi preghiamo di contattarci: saremo lieti di aiutarvi nella ricerca della migliore combinazione*

part n°	description / descrizione	hose size (dash)	hose size (inch)	hose size (dn)	hose ID (mm)	hose OD (mm)	WP (bar)	WP (psi)	BP (bar)	BP (psi)	ferrule part n°	ferrule material	crimping diameter (mm)	crimping diameter (inch)	bore collapse (mm)	bore collapse (inch)	go/nogo gauge	dies set * (mm)
155X - R18 CPLT 3000 NC - CONSTANT PRESSURE LOW TEMP NON CONDUCTIVE																		
1551	3/16 R18 CPLT 3000 NC - CONSTANT PRESSURE LOW TEMP NON CONDUCTIVE	-3	3/16	DN5	5,00	9,60	210	3.000	840	12.000	SAB111	Carbon Steel	11,80	0,465	0,30	0,0118	N/A	10
											SAB811	Stainless Steel (A316L)	11,80	0,465	0,30	0,0118		
1552	1/4 R18 CPLT 3000 NC - CONSTANT PRESSURE LOW TEMP NON CONDUCTIVE	-4	1/4	DN6	6,50	12,20	210	3.000	840	12.000	SAB121	Carbon Steel	14,40	0,567	0,30	0,0118	N/A	14
											SAB821	Stainless Steel (A316L)	14,40	0,567	0,30	0,0118		
1553	5/16 R18 CPLT 3000 NC - CONSTANT PRESSURE LOW TEMP NON CONDUCTIVE	-5	5/16	DN8	8,10	14,30	210	3.000	840	12.000	SAB131	Carbon Steel	16,80	0,661	0,30	0,0118	N/A	16
											SAB831	Stainless Steel (A316L)	16,80	0,661	0,30	0,0118		
1554	3/8 R18 CPLT 3000 NC - CONSTANT PRESSURE LOW TEMP NON CONDUCTIVE	-6	3/8	DN10	9,70	16,60	210	3.000	840	12.000	SAB141	Carbon Steel	18,80	0,740	0,30	0,0118	N/A	16
											SAB841	Stainless Steel (A316L)	18,80	0,740	0,30	0,0118		
1555	1/2 R18 CPLT 3000 NC - CONSTANT PRESSURE LOW TEMP NON CONDUCTIVE	-8	1/2	DN12	13,00	22,50	210	3.000	840	12.000	SA5151	Carbon Steel	25,00	0,984	0,50	0,0197	N/A	23
											SA5851	Stainless Steel (A316L)	25,00	0,984	0,50	0,0197		
1556	5/8 R18 CPLT 3000 NC - CONSTANT PRESSURE LOW TEMP NON CONDUCTIVE	-10	5/8	DN16	16,30	26,10	210	3.000	840	12.000	SA5161	Carbon Steel	30,50	1,201	0,70	0,0276	N/A	27
											SA5861	Stainless Steel (A316L)	30,50	1,201	0,70	0,0276		