



056 - 1SB - 一层钢丝编织海事管

Transfer Oil reserve the rights to introduce improving modifications whenever necessary.

The listed crimping data have been developed in Transfer Oil R&D laboratories and refer to tests carried out on thermoplastic hoses manufactured by Transfer Oil, and specific Transfer Oil approved ferrules and fittings.

Such values are anyway to be considered advisory and not binding for Transfer Oil because the impossibility to consider technical variability like the swaging machine used, the set of crimping dies used, the speed of the crimping process, the tolerances of each single item involved, etc.

For new applications or for hoses, ferrules and fittings not listed in this file please contact us, and we will be happy to help you in finding the best match.

Part no.	Description	Dash	Inches	DN	ID (mm)	OD (mm)	WP (bar)	WP (psi)	BP (bar)	BP (psi)	Ferrule part n°	Ferrule material	Crimping diameter (mm)	Crimping diameter (inch)	Bore collapse (mm)	Bore collapse (inch)	go/nogo gauge	dies set* (mm)
0561	3/16 1SB MARINER	-3	3/16	DN5	5.0	9.7	360	5200	1440	20800	SAB811	Stainless Steel (A316L)	12.1	0.476	0.3	0.0118	N/A	12
0561	3/16 1SB MARINER	-3	3/16	DN5	5.0	9.7	360	5200	1440	20800	SAB111	Carbon Steel	12.1	0.476	0.3	0.0118	N/A	12
0562	1/4 1SB MARINER	-4	1/4	DN6	6.5	11.7	310	4500	1240	18000	SAB821	Stainless Steel (A316L)	14.4	0.567	0.3	0.0118	N/A	14
0562	1/4 1SB MARINER	-4	1/4	DN6	6.5	11.7	310	4500	1240	18000	SAB121	Carbon Steel	14.4	0.567	0.3	0.0118	N/A	14
0563	5/16 1SB MARINER	-5	5/16	DN8	8.1	13.2	250	3600	1000	14400	SAB831	Stainless Steel (A316L)	16.4	0.646	0.3	0.0118	N/A	16
0563	5/16 1SB MARINER	-5	5/16	DN8	8.1	13.2	250	3600	1000	14400	SAB131	Carbon Steel	16.4	0.646	0.3	0.0118	N/A	16
0564	3/8 1SB MARINER	-6	3/8	DN10	9.8	15.5	225	3200	900	12800	SAB841	Stainless Steel (A316L)	18.5	0.728	0.3	0.0118	N/A	16
0564	3/8 1SB MARINER	-6	3/8	DN10	9.8	15.5	225	3200	900	12800	SAB141	Carbon Steel	18.5	0.728	0.3	0.0118	N/A	16
0565	1/2 1SB MARINER	-8	1/2	DN12	13.0	18.8	190	2700	760	10800	SAB851	Stainless Steel (A316L)	21.8	0.858	0.5	0.0197	N/A	19
0565	1/2 1SB MARINER	-8	1/2	DN12	13.0	18.8	190	2700	760	10800	SAB151	Carbon Steel	21.8	0.858	0.5	0.0197	N/A	19
0566	5/8 1SB MARINER	-10	5/8	DN16	16.3	22.0	140	2000	560	8000	SAB861	Stainless Steel (A316L)	25.4	1.000	0.5	0.0197	N/A	23
0566	5/8 1SB MARINER	-10	5/8	DN16	16.3	22.0	140	2000	560	8000	SAB161	Carbon Steel	25.4	1.000	0.5	0.0197	N/A	23
0567	3/4 1SB MARINER	-12	3/4	DN20	19.5	25.8	115	1600	460	6400	SAB871	Stainless Steel (A316L)	29.1	1.146	0.5	0.0197	N/A	27
0567	3/4 1SB MARINER	-12	3/4	DN20	19.5	25.8	115	1600	460	6400	SAB171	Carbon Steel	29.1	1.146	0.5	0.0197	N/A	27
0568	1 1SB MARINER	-16	1	DN25	25.8	33.4	95	1300	380	5200	SAB881	Stainless Steel (A316L)	37.4	1.472	0.5	0.0197	N/A	36
0568	1 1SB MARINER	-16	1	DN25	25.8	33.4	95	1300	380	5200	SAB181	Carbon Steel	37.4	1.472	0.5	0.0197	N/A	36

* The dies set indicated are a standard die set for FinnPower FP20 swaging machine, as used in the R&D laboratory of Transfer Oil, used to verify the swaging parameters.